

TEST ITEM	RESULT (BATCH/LOT NO.)	TEST METHOD
	313037	
MI g/10 min	0.64	ASTM D 1238
MI (5.0) g/10 min	1.8	ASTM D 1238
DENSITY g/cm ³	0.934	ASTM D 792
YI	1.0	SKTM-G-801
APPEARANCE	NORMAL	SKTM-G-805
LONG > 4MESH wt%	0.0	SKTM-G-805
FINE < 20MESH wt%	0.01	SKTM-G-805
PEL >=11 ea/kg	0	SKTM-G-805
PEL 3-10 ea/kg	0	SKTM-G-805
D/C PELLETT ea/kg	12	SKTM-G-805
FOREIGN BODY ea/kg	0	SKTM-G-805
FRAY >=1CM ea/kg	0	SKTM-G-805
FRAY < 1CM ea/kg	0	SKTM-G-805
BS, >=2MM ea/kg	0	SKTM-G-805
BS, < 2MM ea/kg	0	SKTM-G-805
Bulk Density g/cm ³	0.511	SKTM-G-501
P/IRREGULARITY	8.4	SKTM-G-802