

SEETEC EVA VA910
 Ethylene Vinyl Acetate Copolymer
 Lotte Daesan Petrochemical Corp.



Prospector

General

Material Status	• Commercial: Active		
Availability	• Asia Pacific	• Europe	• North America
Features	• Good Adhesion	• Good Processability	
Uses	• Adhesives		
Forms	• Pellets		

Physical

	Nominal Value Unit	Test Method
Density	0.950 g/cm ³	ASTM D1505
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	400 g/10 min	ASTM D1238

Hardness

	Nominal Value Unit	Test Method
Durometer Hardness (Shore D)	18	ASTM D2240

Thermal

	Nominal Value Unit	Test Method
Vicat Softening Temperature	40.0 °C	ASTM D1525
Melting Temperature	65.0 °C	DSC

Notes

¹ Typical properties: these are not to be construed as specifications.

Revision History

Document Created: Saturday, December 31, 2011
 Added to Prospector: October, 2004
 Last Updated: 12/18/2007